

# VISTANEX<sup>®</sup> LM POLYISOBUTYLENE

**ExxonMobil**  
Chemical

## Vistanex LM - Regular Grades

Low molecular weight, polyisobutylene polymers

Effective: March 1998

CAS #9003-27-4

### Product Sales Specification

Grades	Vistanex LM-MS	* Vistanex LM-MH	Test Methods
Appearance	Water white to dark amber*		AMS 83-006
	Free of foreign matter		
Penetration, mm @ 25°C	19.9 - 15.5	15.4 - 11.5	AMS 210-10
Non-Volatile Matter, wt% Vacuum oven, 4 hrs. @ 300°F	97.0 min		AMS 82-003

### Typical Properties

Specific Gravity, 20/20 °C	0.91		ASTM D 792
Density			
@ 23°C, kg/m3	914		-
@ 73°F, lb/USG	7.63		-
Brookfield Viscosity, cps @ 350°F	25,000 to 35,000	50,000 to 70,000	ASTM D 3236
Staudinger Molecular Weight	10,700	11,900	AMS 77-005
Flory Molecular Weight	45,000	53,000	AMS 77-005

\* ExxonMobil Chemical Company color scale. Product may be very hazy and contain numerous black specks (more than 15 particles of carbonized polymer per 100 lb. drum.)

Product sales specifications were developed pursuant to ExxonMobil testing and sampling procedures. Procedures available upon request. Specification and/or procedures are subject to change without notice unless otherwise agreed to in writing.

Format update: January 2000

©2000 ExxonMobil. The user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Typical values only represent the values one would expect if the property were tested in our laboratories with our test methods on the specified data. Some product properties are not frequently measured, and accordingly typical values are not based upon a statistically relevant number of tests. Specifications are pursuant to ExxonMobil Chemical's sampling and testing procedures in effect at the time of production. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use and any process. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no warranty against patent infringement, nor any endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. The ExxonMobil Chemical Emblem, the "Interlocking X" Device and Vistanex are trademarks of Exxon Mobil Corporation.

# VISTANEX<sup>®</sup> LM POLYISOBUTYLENE

**ExxonMobil**  
Chemical

## Vistanex LM - LC (Low Color) Grades

Low molecular weight, low color polyisobutylene polymers

Effective: March 1998

CAS #9003-27-4

### Product Sales Specification

Grades	Vistanex LM-MS-LC	Vistanex LM-MH-LC	Vistanex LM-H-LC	Test Methods
Appearance	Water white to pale yellow*			AMS 83-006
	Free of foreign matter			
Penetration, mm @ 25°C	19.9 - 15.5	15.4 - 11.5	11.4 - 9.0	AMS 210-10
Non-Volatile Matter, wt%	97.0 min			AMS 82-003
Vacuum oven, 4 hrs. @ 300°F				

### Typical Properties

Specific Gravity, 20/20 °C	0.91			ASTM D 792
Density				
@ 23°C, kg/m3	914			-
@ 73°F, lb/USG	7.63			-
Brookfield Viscosity, cps	25,000 to 35,000	50,000 to 70,000	80,000 to 150,000	ASTM D 3236
@ 350°F				
Staudinger Molecular Weight	10,700	11,900	13,300	AMS 77-005
Flory Molecular Weight	45,000	53,000	63,000	AMS 77-005

\* ExxonMobil Chemical Company color scale. Product may have a slight haze and contain some black specks (up to 15 particles of carbonized polymer per 100 lb. drum.)

Product sales specifications were developed pursuant to ExxonMobil testing and sampling procedures. Procedures available upon request. Specification and/or procedures are subject to change without notice unless otherwise agreed to in writing.

Format update: January 2000

©2000 ExxonMobil. The user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Typical values only represent the values one would expect if the property were tested in our laboratories with our test methods on the specified date. Some product properties are not frequently measured, and accordingly typical values are not based upon a statistically relevant number of tests. Specifications are pursuant to ExxonMobil Chemical's sampling and testing procedures in effect at the time of production. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use and any process. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no warranty against patent infringement, nor any endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. The ExxonMobil Chemical Emblem, the "Interlocking X" Device and Vistanex are trademarks of Exxon Mobil Corporation.